artisan EXTERIOR

WALL

ALL FORMATS

Technical Specification Guide

Table of Contents

Introduction 4-5
Product Reference Images 6-17
Organic 6-8
Modular 9
Vertical & Linear 10
Z Panel 11
Capping 12-13
Format & Pattern Reference Images 14-17
Technical Details 17-29
Organic 18-23
Bribie 18
Callala 18
Chateau 18
Cordillera 19
Cottage 19
Culburra 19-20
Estate 20
Heritage 20
Jaiba 21
Lavato 21
Luna 21
Mesa 22
Peak 22
Pinnacle 22
Satula 23
Terra 23
Vale 23
Modular 24-25
Gama 24
Grange 24
Noir 24-25
Ridge 25
Summit 25
Vertical & Linear 26-27
Areia 26
Calcario 26
Fosca 26
Preikestolen 27

Table of Contents

Z Panel 28-29

Rustic Granite 28

Rustic Grey 28

Rustic Mica 29

Start with the perfect finish.

Our wall cladding collection highlights the raw beauty of natural quartzite, sandstone, granite, and limestone. With rich textures and organic variation, each piece is designed to add depth and character to any outdoor space.

Available in organic, modular, linear, vertical, and Z-panel formats, our cladding can be dry-stacked or grouted to suit your design vision. Distinctive finishes such as split, bush-hammered, and sandblasted further enhance the natural appeal. Capping and corner pieces ensure a seamless finish, giving your project a polished and cohesive look.

The colour palette spans from the light, minty whites of Jaiba, soft coastal creams with rust tones of Bribie, to the deep earthen charcoal hues of Noir. This diverse spectrum offers an array of options, allowing you to find the perfect match for any project, whether modern or traditional in style

Crafted for lasting impact, our wall cladding can be viewed installed in our ACT, NSW, and QLD studios, open Monday to Saturday. Samples are also available to support your selection.

This document provides the technical specifications to guide your choice. For further details, our team is here to assist.

Organic Stone Wall Cladding
Callala (Sandstone)

Modular Stone Wall Cladding
Ridge (Sandstone)



Vertical Stone Wall Cladding
Preikestolen (Granite)



Linear Stone Wall Cladding
Calcario (Limestone)



Z Panel Stacked Stone Wall Cladding
Rustic Mica (Quartzite)

Natural Stone Wall Cladding

ORGANIC

BRIBIE (Sandstone)

CALLALA (Sandstone)



CHATEAU (Granite)

CORDILLERA (Marble & Quartzite)

COTTAGE (Quartzite)

CULBURRA (Sandstone)

Natural Stone Wall Cladding

ORGANIC (Continued)

ESTATE (Granite)

HERITAGE (Quarzite)

JAIBA (Sandstone)

LAVATO (Quartzite)

LUNA (Quartzite)

MESA (Slate)

Natural Stone Wall Cladding

ORGANIC (Continued)

PEAK (Quartzite)

PINNACLE (Quartzite)

SATULA (Slate & Quartzite)

TERRA (Sandstone)

VALE (Travertine)

Natural Stone Wall Cladding

MODULAR

GAMA (Sandstone)

GRANGE (Sandstone)

NOIR (Limestone)

RIDGE (Sandstone)



SUMMIT (Quartzite)

Natural Stone Wall Cladding

VERTICAL & LINEAR

AREIA (Granite)

CALCARIO (Limestone)

FOSCA (Limestone)

PREIKESTOLEN (Granite)

Natural Stone Wall Cladding

Z PANEL

RUSTIC GRANITE (Granite)

RUSTIC GREY (Quartzite)

RUSTIC MICA (Quartzite)

Natural Stone Wall Cladding

CAPPING

CAPRI (Limestone)

COTTAGE (Quartzite)

ESTATE (Granite)

GRANGE (Sandstone)

HERITAGE (Quartzite)

KAHVI (Limestone)

Natural Stone Wall Cladding

CAPPING

NOIR (Limestone)

RIDGE (Sandstone)

RUSTIC GREY (Quartzite)

SOKERIA (Limestone)

Formats & Patterns

ORGANIC



Random size, grouted



Random size, dry stacked



Random size linear, dry stacked

Formats & Patterns

MODULAR



Random size, grouted



Random size, dry stacked

Formats & Patterns

VERTICAL & LINEAR

Coursed height pieces



Vertical modular pieces

Formats & Patterns

Z-PANEL



Panel



Corner

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Bribie - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
48.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	69kg/m²	20m²	Split top and edges
Corners			
Random Size	20kg/Lm	25Lm	Split top and edges

Callala - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
48.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	60kg/m²	20m²	Split top and edges
Corners			
Random Size	20kg/Lm	25Lm	Split top and edges

Chateau - Granite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
56.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	80kg/m²	15m²	Split top and edges
Corners			
Random Size	20kg/Lm	20Lm	Split top and edges

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Cordillera - Marble & Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
<1%	194	15.1	0.30%	1.20%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	58kg/m²	20m²	Split top and Organic Edges
Corners			
Random Size	20kg/Lm	30Lm	Split top and Organic Edges

Cottage - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	76kg/m²	15m²	Split top and edges
Corners			
Random Size	16.2kg/Lm	20Lm	Split top and edges
Capping			
600x300x35-60mm	20kg each	50Pcs	Split Top & Rock-faced Long Edges

Culburra - Limestone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
<1%	194	15.1	0.30%	1.20%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	60kg/m²	20m²	Sawn and Tumbled

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Culburra - Limestone (continued)

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Corners			
Random Size	20kg/Lm	30Lm	Sawn & Tumbled

Estate - Granite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
56.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	66kg/m²	15m²	Split top and edges
Corners			
Random Size	16.2kg/Lm	20Lm	Split top and edges
Capping			
600x300x35-60mm	21.5kg each	50Pcs	Split Top & Rock-faced Long Edges

Heritage - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
0.64%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	65kg/m²	10m²	Split top and edges
Corners			
Random Size	22kg/Lm	25Lm	Split top and edges
Capping			
600x300x35-60mm	20kg each	50Pcs	Split Top & Rock-faced Long Edges

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Jaiba - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
95.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	65kg/m²	10m²	Split top and edges
Corners			
Random Size	22kg/Lm	25Lm	Split top and edges

Lavato - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
94.00%	20.53 Mpa	15.81 Mpa	0.34%	1%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size [25-40mm thickness]	72kg/m²	11m²	Split top and edges

Luna - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
6.77%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	83kg/m²	12m²	Split top and edges
Corners			
Random Size	40kg/Lm	30Lm	Split top and edges

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Mesa - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size [20-40mm thickness]	69kg/m²	15m²	Split & Tumbled
Corners			
Random Size [20-40mm thickness]	20kg/Lm	25Lm	Split & Tumbled

Peak - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%

58.00

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size [20-40mm thickness]	69kg/m²	15m²	Split & Tumbled
Corners			
Random Size [20-40mm thickness]	20kg/Lm	25Lm	Split & Tumbled

Pinnacle - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%

58.00%

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size - Linear	78kg/m²	15m²	Split top and edges
Corners			
Random Size	16kg/Lm	25Lm	Split top and edges

Organic

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Satula - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
<1%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size - Linear	69kg/m²	15m²	Split top and edges
Corners			
Random Size	20kg/Lm	20Lm	Split top and edges

Terra - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
6.77%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	83kg/m²	10m²	Natural Split top and edges
Corners			
Random Size	40kg/Lm	28Lm	Natural Split top and edges

Vale - Travertine

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
<1%	50	7.7	1.20%	7%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Size	58kg/m²	20m²	Split top and edges
Corners			
Random Size	20kg/Lm	30Lm	Split top and edges

Modular

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Gama - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
6.77%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Loose	60kg/m²	20m²	Split top and edges
Corners			
Loose	40kg/m²	30Lm	Split top and edges

Grange - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Loose	80kg/m²	15m²	Split top and edges
Corners			
Loose	20kg/Lm	25Lm	Split top and edges
Capping			
600x300x35-60mm	12kg each	75Pcs	Split Top + Split Long Edges

Noir - Limestone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
1%	109 Mpa	15.9 Mpa	0.21%	0.20%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Random Square Size	75kg/m²	13.2m² [0.44m²/Box]	Split top and edges

Modular

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Noir - Limestone (Continued)

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Corners			
Loose	16.2kg/Lm	25Lm [0.6Lm/Box]	Split top and edges
Capping			
600x300x35-50mm	20kg each	50Pcs	Honed Top & Split Long Edges

Ridge - Sandstone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
45%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Loose	80kg/m²	10m²	Split top and edges
Corners			
Loose	20kg/Lm	20Lm	Split top and edges
Capping			
600x300x35-60mm	12kg each	75Pcs	Split Top & Rock Faced Long Edges

Summit - Quartzite

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
58%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Loose	74kg/m²	15m²	Split & Tumbled
Corners			
Loose	16kg/Lm	25Lm	Split & Tumbled

Vertical & Linear

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Areia - Granite (*Linear*)

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
68%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Coursed Height Pieces [300mm & 400mm] Random Length	69kg/m²	14m² [2.8m² /set]	Varying henpecked & sandblasted surfaces

Calcario - Limestone (*Linear*)

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
2.16%	105 MPa	15.4 MPa	0.91%	2.02%	105.00%	41.80%

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Coursed Height Pieces [300mm & 400mm] Random Length	95kg/m²	4.18-6.75m²	Varying henpecked, split, rock-faced & sandblasted surfaces.
Corners			
Coursed Height Pieces [300mm & 400mm] Random Length	38kg/Lm	6.6Lm	Varying henpecked, split, rock-faced & sandblasted surfaces..

Fosca - Limestone (*Vertical & Linear*)

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
3%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Coursed Height Pieces [300mm& 400mm] Random Length	95kg/m²	12-16m²	Varying Finishes

Vertical & Linear

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Fosca - Limestone (*Vertical & Linear) (Continued)*

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Corners			
Coursed Height Pieces [300mm & 400mm] Random Length	38kg/Lm	14.1-20Lm	Varying Finishes

Preikestolen - Granite (*Vertical)*

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
75%	191.5 Mpa	15.6 Mpa	0.30%	0.90%		

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Vertical Modular Pieces, Random Heights, 400, 330, 260, 175 Widths	1063kg/Set	6.38m² [28Pcs/set]	Split surface top and bottom edges, swan cut edges

Z Panel

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Rustic Granite (Granite)

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
56.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Z-Panel 600x200x25-40mm	81kg/m²	10.56m²	Split Face, Cement Backing
Corners			
Z-Corner Long Side 360/310x200x25-40mm Short Side 110/160x200x25-40mm	9kg each	80Pcs	Split Face, Cement Backing

** Estate Capping recommended*

Rustic Grey (Quartzite)

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
22.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Z-Panel 600x200x25-40mm	81kg/m²	10.56m²	Split Face, Cement Backing
Corners			
Z-Corner Long Side 360/310x200x25-40mm Short Side 110/160x200x25-40mm	9kg each	80Pcs	Split Face, Cement Backing
Capping			
600x300x35-60mm	20kg each	50Pcs	Split Top + Rock-faced Long Edges

Z Panel

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Rustic Mica (Quartzite)						
Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
56.00%						

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Cladding			
Z-Panel 600x200x25-40mm	81kg/m²	10.56m²	Split Face, Cement Backing
Corners			
Z-Corner Long Side 360/310x200x25-40mm Short Side 110/160x200x25-40mm	9kg each	80Pcs	Split Face, Cement Backing
			** Cottage Capping recommended*

Additional Capping

* Please enquire with us to confirm stock availability. Custom sizes are available by order. Weights are indicative only and exclude packaging *

Kahvi Capping - Limestone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
2.16%	105	15.4	0.91	2.02	102	41.60

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Capping			
600x300x40mm	28kg each	50Pcs	Split on 2 Long Edges, Sawn Bottom & Sawn on 2 Short Edges

Sokeria Capping - Limestone

Crystalline Silica	Strength		Absorption		SRI	
	Compressive	Flexural	Water Porosity	Open Porosity	Solar Index	Solar Reflectance
%	Mpa	Mpa	%	%	SRI	%
2.16%	105	15.4	0.91	2.02	104	40.60

Format mm	Weight UOM	Pack Volumes per crate	Surface Finish
Capping			
600x300x40mm	28kg each	50Pcs	Split on 2 Long Edges, Sawn Bottom & Sawn on 2 Short Edges

1300 301 898
artisanexterior.com.au